



Datasheet

EPDM Black Cellular

Algemene Rubberindustrie Eindhoven BV

Hooge Zijde 25

5626 DC EINDHOVEN

040-2904999

info@are-rubber.nl

www.are-rubber.nl

EPDM Black Cellular

PROPERTIES	TEST METHOD	UNIT	DEFAULT	ACTUAL
DENSITY	ISO 2781	g/cm ³	0,30 +/-0,1	0.3
COMPRESSION SET (50% COMP) AFTER 22H/23°C	ASTM D1056	%	max 25	7
COMPRESSION SET (50% COMP) AFTER 22H/70°C	ASTM D1056	%	max 60	36
COMPRESSION DEFLECTION 25%	ASTM D1056	kN/m ²	50 +/-15	52
COMPRESSION DEFLECTION 25%, CHANGE AFTER 168H/70°C	ASTM D1056	%	max +/-30	4
WATER ABSORPTION	ASTM D1056	%	max 5	4
ADDITIONAL INFORMATION				
THE ACTUAL VALUES ARE TYPICAL TARGET VALUES OF THE MATERIAL AND MAY BE SUBJECT TO FLUCTUATIONS.				